# **3M** Electrical Tape 92 Polyimide Film Tape With Thermosetting Silicone Adhesive

# Data Sheet



## **Product Description**

 $3M^{\text{TM}}$  Electrical Tape 92 is a 1-mil polyimide film backing with silicone adhesive.

- 1-mil polyimide Kapton<sup>™</sup> backing
- Silicone adhesive
- High temperature applications to 180°C
- UL510 Flame Retarded

Like all 3M insulating tapes, 3M 92 Tape is available in standard and custom widths and lengths. Standard length is 36 yards.

- Widths from 1/4" to 23"
- Longer lengths up to several times normal length, dependent upon width. Check with Customer Service.

#### Applications

3M Electrical Tape 92 is used for high temperature electrical applications in which a tough, thin insulating material is required for wrapping coils, transformers, capacitors and wire harnesses. It is also used in printed circuit board assembly as a wave solder masking tape.

## **UL Component Recognition**

UL Recognized Flame Retarded per UL510. UL File Number E17385, Guide OANZ2. Underwriters Laboratories (UL) Recognized products are evaluated for use as components of end-product equipment that is Listed or Classified by UL. To achieve Underwriters Laboratories Recognition, component construction must meet UL specifications and conditions of acceptability for proper and safe use of the component or products.

| Typical Properties                           | Typical Values         |
|--|------------------------|
| Adhesive                                     | Thermosetting Silicone |
| Backing                                      | Polyimide film         |
| Backing Thickness <sup>1</sup>               | 1.0 mil (0.025mm)      |
| Total Thickness <sup>1</sup>                 | 3.0 mils (0.076mm)     |
| Insulation Resistance <sup>1</sup> (megohms) | > 1 x 10 <sup>6</sup>  |
| Dielectric Breakdown <sup>1</sup>            | 7,500 Volts            |
| Breaking Strength <sup>1</sup>               | 30 lbs./in (53N/10mm)  |
| Elongation <sup>1</sup> (% at break)         | 55%                    |
| Electrolytic Corrosion Factor <sup>3</sup>   | 1.0                    |
| Adhesion to Steel <sup>1</sup>               | 25 oz/in (2.8N/10mm)   |
| UL510 Flame Retarded <sup>2</sup>            | Yes                    |
| Printable                                    | Yes                    |

Note: Typical properties are not recommended for specification purposes. Product specifications will be provided upon request.

Footnote: <sup>1</sup> Test Method ASTM D 1000

<sup>2</sup> UL recognized for flame retardancy per UL510, Product Category OANZ2, File E17385.

<sup>3</sup> 3M Test Method – Available on request.

3M is a trademark of 3M Company. Other trademarks used herein are the properties of their respective owners.

#### Important Notice

Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use.

Warranty; Limited Remedy; Limited Liability. This product will be free from defects in material and manufacture as of the date of purchase. 3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. Except where prohibited by law, 3M will not be liable for any loss or damage arising from this 3M product, whether direct, Indirect, special, Incidental or consequential regardless of the legal theory asserted.



#### **Electrical Products Division**

6801 River Place Blvd. Austin, TX 78726-9000 www.3M.com/elpd

© 3M 2004 78-8125-9924-5-B